



RSP-140

SUPER POLYESTER PRIMER SURFACER

Technical Data Sheet
Technical Hotline 800.735.0303

PRODUCT

RSP-140


DESCRIPTION

SUPER POLYESTER PRIMER SURFACER - GREY



DESCRIPTION

RSP-140 Super Polyester Primer Surfacer is a two component, high solid, high build primer offering exceptional filling characteristics and superior topcoat holdout with ease of application. Enhanced flow and leveling properties combine with an improved cross-linking density to effectively lock down body repairs setting the stage for a flawless finish.



MIXING

Shake before mixing. Mix 2% by weight.



APPLICATION

Apply 2-3 wet coats, allowing a 10-15 minute flash between coats at 75°F. Use a primer gun with a 1.6 - 2.0 fluid nozzle/air cap. Allow RSP-140 to dry 1 hour per coat at 75° F before sanding.



DRYING AT 75° F.

TO FLASH	10-15 MINUTES (BETWEEN COATS)
TO SAND	1 HOUR (PER COAT)
TO TOPCOAT	1 HOUR (PER COAT)



FORCE DRYING

FLASH TIME @ 77° F	10 MINUTES
BAKE TIME @ 140° F	30 MINUTES

TECHNICAL DATA

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
RSP-140	2.9	344	2.2	261
ACTIVATOR TUBE	0.2	20	0.1	6
V.O.C. (RTS):				
RSP-140/ ACTIVATOR TUBE	1.6	186	1.2	141

Weight Solids: 74.88%
Film Build: 2.0 - 3.0 mils per coat
Coverage: 1200 sq. ft. per gallon at 1 dry mil

Manufacturer's Exclusive Limited Warranty

For Industrial use only by professional, trained personal using proper safety protective equipment. Not for sale to, or use by, the general public. Manufacturer warrants that its products are free from defect in material and workmanship at the time of sale. In the event that any product is proved by objective testing and analysis to have been defective at the time of sale, upon the return of the defective product, the manufacturer shall replace the product at no cost, excluding the shipping costs, as the exclusive remedy. This warranty does not cover damage caused by accident, misuse, improper application, improper combination of products or tampering. ALL IMPLIED WARRANTIES WHETHER IT BE OF MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. THIS WARRANTY EXCLUDES ALL INCIDENTAL AND CONSEQUENTIAL DAMAGES.

NOTE: Refinish Solutions products are not recommended for use in temperatures below 60° F.

Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read MSDS Before Use

Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE MSDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.