



RSP-130

2.1 VOC PRIMER SURFACER

Technical Data Sheet
Technical Hotline 800.735.0303

PRODUCT#

RSP-130
RSA-135

DESCRIPTION

2.1 VOC PRIMER SURFACER
2.1 VOC PRIMER SURFACER ACTIVATOR



DESCRIPTION

RSP-130 is a 2.1 VOC Urethane Primer Surfacer formulated for quick filling, easy sanding and excellent color holdout under a wide range of shop conditions. RSP-130 provides the high performance you expect from a high build primer surfacer and features a 4:1 mix ratio.



MIXING

RSP-130 **TO** RSA-135
4 Parts 1 Part



APPLICATION

Apply 2-3 wet coats allowing 15 minutes between coats. Allow RSP-130 to dry 4-6 hours at 77° F before sanding.



DRYING AT 77° F

FLASH	15 MINUTES
TO SAND	4-6 HOURS
TO TOPCOAT	4-6 HOURS



FORCE DRYING

FLASH TIME @ 77° F	15 MINUTES
BAKE TIME @ 140° F	30 MINUTES



REPAIRING & RECOATING

RSP-130 **must be** sanded prior to recoating after a 4-6 hour dry at 77° F, or after a minimum 1 hour cool down after force drying at 140° F for 30 minutes.

TECHNICAL DATA

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
RSP-130	1.9	232	1.3	156
RSA-135	3.2	379	1.0	119
V.O.C. (RTS):				
RSP-130/RSA-135	2.1	247	1.2	149

Weight Solids: 61%

Film Build: 1.3 - 1.5 mils per full wet coat

Coverage: 688 sq. ft. per gallon at 1 dry mil

Manufacturer's Exclusive Limited Warranty

For Industrial use only by professional, trained personal using proper safety protective equipment. Not for sale to, or use by, the general public. Manufacturer warrants that its products are free from defect in material and workmanship at the time of sale. In the event that any product is proved by objective testing and analysis to have been defective at the time of sale, upon the return of the defective product, the manufacturer shall replace the product at no cost, excluding the shipping costs, as the exclusive remedy. This warranty does not cover damage caused by accident, misuse, improper application, improper combination of products or tampering. ALL IMPLIED WARRANTIES WHETHER IT BE OF MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. THIS WARRANTY EXCLUDES ALL INCIDENTAL AND CONSEQUENTIAL DAMAGES.

NOTE: Refinish Solutions products are not recommended for use in temperatures below 60° F.

Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read SDS Before Use

Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.