



RSP-160

FAST BUILD URETHANE PRIMER

Technical Data Sheet
Technical Hotline 800.735.0303

PRODUCT#

RSP-160
RSA-165


DESCRIPTION

FAST BUILD URETHANE PRIMER
URETHANE PRIMER ACTIVATOR



DESCRIPTION

RSP-160 Fast Build Urethane two part primer surfacer sprays and sands easily, builds quickly and dries fast to a high quality durable finish that minimizes scratch swelling.



MIXING

RSP-160 TO RSA-165
4 Parts 1 Part



APPLICATION

Apply 2-3 wet coats allowing 10-15 minutes between coats. Allow RSP-160 to dry 2-4 hours at 77° F before sanding. For optimum performance apply RSS-150 Ready To Spray Sealer Grey before topcoating.



DRYING AT 77° F

FLASH	10-15 MINUTES
TO SAND	2-4 HOURS
TO TOPCOAT	2-4 HOURS

FORCE DRYING

FLASH TIME @ 77° F	15 MINUTES
BAKE TIME @ 140° F	40 MINUTES

TECHNICAL DATA

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
RSP-160	3.6	432	3.3	392
RSA-165	5.9	713	5.9	713
V.O.C. (RTS):				
RSP-160/RSA-165	4.1	493	3.8	456

Manufacturer's Exclusive Limited Warranty

For Industrial use only by professional, trained personal using proper safety protective equipment. Not for sale to, or use by, the general public. Manufacturer warrants that its products are free from defect in material and workmanship at the time of sale. In the event that any product is proved by objective testing and analysis to have been defective at the time of sale, upon the return of the defective product, the manufacturer shall replace the product at no cost, excluding the shipping costs, as the exclusive remedy. This warranty does not cover damage caused by accident, misuse, improper application, improper combination of products or tampering. ALL IMPLIED WARRANTIES WHETHER IT BE OF MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. THIS WARRANTY EXCLUDES ALL INCIDENTAL AND CONSEQUENTIAL DAMAGES.

NOTE: Refinish Solutions products are not recommended for use in temperatures below 60° F.

Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read SDS Before Use

Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.